

# Performance Characteristics Sheet

EFFECTIVE DATE: October 31, 1995

EDITION NO.: 3

## MANUFACTURER AND MODEL :

Manufacturer: *TN Technologies, Inc. (TN Spectrace)*

Make: *Pb Analyzer*

Model: *9292*

Source:  $^{109}\text{Cd}$

Note: This sheet supersedes all previous sheets for the XRF instrument of the make, model, and source shown above.

## FIELD OPERATION GUIDANCE

### OPERATING PARAMETERS

Nominal Time Reading is 15 seconds.

### XRF CALIBRATION CHECK LIMITS

0.7 to 1.4 (inclusive)
------------------------

### SUBSTRATE CORRECTION:

Not required for any substrate.

### INCONCLUSIVE RANGE OR THRESHOLD

DESCRIPTION	SUBSTRATE	INCONCLUSIVE RANGE in mg/cm <sup>2</sup>	
		LOWER BOUND	UPPER BOUND
Results not corrected for substrate bias	Brick	0.91	1.19
	Concrete	0.91	1.19
	Drywall	0.91	1.19
	Metal	0.91	1.19
	Plaster	0.91	1.09
	Wood	0.91	1.29

## BACKGROUND INFORMATION

### EVALUATION DATA SOURCE AND DATE

This sheet supplements Chapter 7 of the HUD *Guidelines for the Evaluation and Control of Lead-Based Paint Hazards in Housing* ("HUD Guidelines"). Performance parameters shown on this sheet are derived from measurements of real world archived paint samples collected during the EPA/HUD field evaluation study, and from data collected during testing in January 1995 and in September 1995. The field evaluation data were collected from approximately 1,200 test locations using two instruments both with radiation sources installed in April 1993. See *A Field Test of Lead-Based Paint Testing Technologies: Technical Report*,

EPA 747-R-95-002b, May 1995 for further information. The archival testing data were collected from approximately 150 test locations using two instruments. The instrument that was used in January had a radiation source installed in July 1994 and the instrument that was used in September 1995 had a radiation source installed in January 1995. All of the instruments mentioned had 30 mCi initial strengths.

### **OPERATING PARAMETERS**

Performance parameters shown in this sheet are applicable only when properly operating the instrument using the manufacturer's instructions and procedures described in Chapter 7 of the HUD Guidelines.

### **XRF CALIBRATION CHECK**

The calibration of the XRF instrument should be checked using the film nearest  $1.0 \text{ mg/cm}^2$  in the NIST Standard Reference Material (SRM) used (e.g., for NIST SRM 2579, use the  $1.02 \text{ mg/cm}^2$  film).

If readings are outside the acceptable calibration check range, follow the manufacturer's instructions to bring the instruments into control before XRF testing proceeds

### **EVALUATING THE QUALITY OF XRF TESTING**

Randomly select ten testing combinations for retesting from each house or from two randomly selected units in multifamily housing.

Conduct XRF retesting at the ten testing combinations selected for retesting.

Determine if the XRF testing in the units or house passed or failed the test by applying the steps below.

Compute the Retest Tolerance Limit by the following steps:

Determine XRF results for the original and retest XRF readings. Do not correct the original or retest results for substrate bias. In single-family and multi-family housing, a result is defined as a single reading. Therefore, there will be ten original and ten retest XRF results for each house or for the two selected units.

Calculate the average of the original XRF result and retest XRF result for each testing combination.

Square the average for each testing combination.

Add the ten squared averages together. Call this quantity C.

Multiply the number C by 0.0072. Call this quantity D.

Add the number 0.032 to D. Call this quantity E.

Take the square root of E. Call this quantity F.

Multiply F by 1.645. The result is the Retest Tolerance Limit.

Compute the average of all ten original XRF results.

Compute the average of all ten retest XRF results.

Find the absolute difference of the two averages.

If the difference is less than the Retest Tolerance Limit, the inspection has passed the retest. If the difference of the overall averages equals or exceeds the Retest Tolerance Limit, this procedure should be repeated with ten new testing combinations. If the difference of the overall

averages is equal to or greater than the Retest Tolerance Limit a second time, then the inspection should be considered deficient.

Use of this procedure is estimated to produce a spurious result approximately 1% of the time. That is, results of this procedure will call for further examination when no examination is warranted in approximately 1 out of 100 dwelling units tested.

**BIAS AND PRECISION**

Do not use these bias and precision data to correct for substrate bias. These bias and precision data were computed without substrate correction from samples with reported laboratory results less than 4.0 mg/cm<sup>2</sup> lead. There were 88 test locations with a laboratory reported result equal to or greater than 4.0 mg/cm<sup>2</sup> lead. Of these, none had XRF readings less than 1.0 mg/cm<sup>2</sup>. These data are for illustrative purposes only. Bias and precision ranges are provided to show the variability found between machines of the same model.

MEASURED AT	SUBSTRATE	BIAS (mg/cm <sup>2</sup> )	BIAS RANGE <sup>P</sup> (mg/cm <sup>2</sup> )	PRECISION <sup>Q</sup> (mg/cm <sup>2</sup> )	PRECISION RANGE <sup>P</sup> (mg/cm <sup>2</sup> )
0.0 mg/cm <sup>2</sup>	Brick	0.0	( 0.0, 0.0)	0.1	( 0.1, 0.1)
	Concrete	0.0	( 0.0, 0.0)	0.1	( 0.1, 0.1)
	Drywall	0.0	( 0.0, 0.0)	0.1	( 0.1, 0.1)
	Metal	0.0	(-0.1, 0.1)	0.1	( 0.1, 0.1)
	Plaster	0.0	(-0.1, 0.0)	0.1	( 0.1, 0.1)
	Wood	0.0	( 0.0, 0.0)	0.1	(<0.1, 0.1)
0.5 mg/cm <sup>2</sup>	Brick	0.1	( 0.0, 0.2)	0.3	( 0.3, 0.3)
	Concrete	0.1	( 0.0, 0.2)	0.3	( 0.2, 0.3)
	Drywall	0.1	( 0.0, 0.2)	0.3	( 0.1, 0.3)
	Metal	0.1	( 0.0, 0.3)	0.3	( 0.3, 0.3)
	Plaster	0.0	(-0.1, 0.2)	0.3	( 0.1, 0.3)
	Wood	0.1	( 0.1, 0.2)	0.3	( 0.3, 0.3)
1.0 mg/cm <sup>2</sup>	Brick	0.2	( 0.0, 0.4)	0.4	( 0.4, 0.5)
	Concrete	0.2	( 0.0, 0.4)	0.4	( 0.3, 0.5)
	Drywall	0.2	( 0.1, 0.4)	0.4	( 0.2, 0.5)
	Metal	0.2	( 0.0, 0.5)	0.4	( 0.4, 0.5)
	Plaster	0.1	(-0.1, 0.3)	0.4	( 0.1, 0.5)
	Wood	0.3	( 0.1, 0.4)	0.4	( 0.4, 0.5)
2.0 mg/cm <sup>2</sup>	Brick	0.4	( 0.0, 0.7)	0.6	( 0.5, 0.6)
	Concrete	0.3	( 0.0, 0.7)	0.5	( 0.4, 0.6)
	Drywall	0.5	( 0.3, 0.7)	0.5	( 0.3, 0.6)
	Metal	0.4	( 0.0, 0.8)	0.6	( 0.5, 0.6)
	Plaster	0.2	(-0.3, 0.7)	0.5	( 0.1, 0.6)
	Wood	0.5	( 0.3, 0.7)	0.6	( 0.5, 0.6)

<sup>P</sup>Ranges are provided to show the variability between machines of the same model.  
<sup>Q</sup>Precision at 1 standard deviation.

**CLASSIFICATION OF RESULTS**

XRF results are classified as positive if they are greater than the upper boundary of the inconclusive range, and negative if they are less than the lower boundary of the inconclusive range, or inconclusive if in between. The inconclusive range includes both its upper and lower bounds. Earlier editions of this *XRF Performance Characteristics Sheet* did not include both bounds of the inconclusive range as "inconclusive." While this edition

of the Performance Characteristics Sheet uses a different system, the specific XRF readings that are considered positive, negative, or inconclusive for a given XRF model and substrate remain unchanged, so previous inspection results are not affected.

**DOCUMENTATION:**

A document titled *Methodology for XRF Performance Characteristic Sheets* provides an explanation of the statistical methodology used to construct the data in the sheets, and provides empirical results from using the recommended inconclusive ranges or thresholds for specific XRF instruments. For a copy of this document call the National Lead Information Center Clearinghouse at 1-800-424-LEAD.

This XRF Performance Characteristics Sheet is a joint product of the U.S. Environmental Protection Agency (EPA) and the U.S. Department of Housing and Urban Development (HUD). The issuance of this sheet does not constitute rulemaking. The information provided here is intended solely as guidance to be used in conjunction with Chapter 7, Lead-Based Paint Inspection, of the *Guidelines for the Evaluation and Control of Lead-Based Paint Hazards in Housing*. EPA and HUD reserve the right to revise this guidance. Please address questions and comments on this sheet to: Director, Office of Lead Hazard Control (L), U.S. Department of Housing and Urban Development, 451 Seventh St, S.W., Washington, DC 20410.