

July 2001

**CONNECTICUT
SUPPLEMENTAL SPECIFICATIONS
SECTION 7.07**

MEMBRANE WATERPROOFING (WOVEN GLASS FABRIC)

Article 7.07.03 - Construction Methods

1 - Primer: *Delete entire passage and replace with the following:*

Beginning at the low point of the surface to be waterproofed, the primer shall be applied in one coat at a rate of 0.45 L/m². The cure time of the primer shall be as recommended by the manufacturer.